

1.2M 跌落测试报告

1.2M Drop Test Report

Client 委托方	Shenzhen Zhongli lithium energy technology Co., Ltd. 深圳市中锂能源技术有限公司
Add. of Client 委托方地址	3Floor, K Building, Mao Yuan Industrial Park, Huanguan South Road, Guanlan Town, Shenzhen 深圳市观澜镇环观南路茂源工业区 K 栋 3 楼
Samples Description 样品名称	Polymer lithium ion battery 聚合物锂离子电池
Model/Type 型号规格	472228
Testing Laboratory 测试机构	Shenzhen TCT Testing Technology Co., Ltd. 深圳市通测检测技术有限公司 1F, Building 1, Yibaolai Industrial Park, Qiaotou Village, Fuyong Town, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福永桥头亿宝来工业城 1 栋 1 楼
Report No. 报告编号	TCT160309B007-1
Issued Date 发行日期	Mar. 15, 2016
Test Conclusion 测试结论: Shown in the Conclusion of test report. 见检测报告结论页.	

Tested by 主检人: 张丽裙 Sunny Zhang

Approved by 批准人: [Signature]



Inspected by 审核人: 张丽裙 Liz Zhang

Seal of TCT 报告单位 (盖章): _____
Date of Issue 签发日期: 2016. 03. 15

I、SAMPLE DESCRIPTION 样品描述

Product Name 产品名称	Polymer lithium ion battery 聚合物锂离子电池		Sample Model 样品型号	472228	
Manufacturer 制造商	Shenzhen Zhongli lithium energy technology Co., Ltd. 深圳市中锂能源技术有限公司				
Address 地址	3Floor, K Building, Mao Yuan Industrial Park, Huanguan South Road, Guanlan Town, Shenzhen 深圳市观澜镇环观南路茂源工业区 K 栋 3 楼				
Trade Mark 商标	----	Shape 形状	Prismatic 棱形	Packaging dimensions 包装尺寸 (L×W×T)	(35.0×25.0×15.0)cm
Nominal Voltage 标称电压	3.7V	Rated Capacity 额定容量	380mAh 1.41Wh	Battery Number 电池数量	315/PCS
Gross weight per package 每包装件毛重	2.53Kg		Net weight of batteries per package 每包装件锂离子电池的净重	2.2kg/packing	
Receiving Date 接收日期	2016-03-10		Completing Date 完成日期	2016-03-15	

II、STANDARD 标准

Section II of Packing Instructions 965 of 57th DGR Manual of IATA.
IATA《危险品规则》(57 版) 包装说明 965 第 II 章节。


III、TEST ITEM 测试项目

- 1). Drop test 跌落测试
- 2). Packing weight test 包装重量测试

IV、TEST METHOD 测试方法

The package of batteries is dropped from 1.2m, 5times per package. The test floor is concrete floor, each package is capable of withstanding a 1.2 meter drop test in any orientation without damage to cell or batteries contained therein. Without shifting of the contents so as to allow battery to battery (or cell to cell) contact and without release of contents.

电池包装件(或含有电池的包装件)从 1.2 米高度进行跌落,每个包装件 5 次.测试底板为混凝土底板,每一个包装件应能承受在任一方位的 1.2 米跌落测试,并且没有电芯或电池损坏.没有位移导致电池或电芯相互接触,并没有内部物品从箱体漏出.



V、TEST APPARATUS 测试仪器

Serial No. 设备编号	Name of Equipment 设备名称	Model 型号	Calibration Date /Due Date 校准日期/到期日
TC-105	Single-blade drop tester 单翼跌落测试仪器	GX-6050-A	2015. 08. 25
			2016. 08. 24
TC-045	Electronic scale 电子秤	TCM-150	2015. 08. 25
			2016. 08. 24

VI、TEST RESULT 测试结果

1) Drop test 跌落测试


Drop position 跌落位置	Test status 测试情况	Conclusion 结论
Front 前面	Without damage packaging 包装没有损坏	Pass 合格
Bottom 底部	Without damage packaging 包装没有损坏	Pass 合格
Angle 角	Without damage packaging 包装没有损坏	Pass 合格
Side 侧面	Without damage packaging 包装没有损坏	Pass 合格
Top 顶部	Without damage packaging 包装没有损坏	Pass 合格

2) Packing weight test 包装重量测试

No. 编号	Test item 测试项目	Weight 重量 (kg)	Remark 备注
1	Packing weight test 包装重量测试	2.53	---

Photos 照片

Samples 样品:



Equipment 设备:



Package 包装:



注意事项

Important Notice

1. The test report is invalid without the official stamp of TCT and Paging seal of TCT.
本报告书无 TCT 盖章、骑缝章无效。
2. Nobody is allowed to photocopy or partly photocopy this test report without written permission of TCT.
未经 TCT 书面同意，不得部分地复制本报告书。
3. The test report is invalid without the signatures of Ratifier, Reviewer and Testing engineer.
本报告书无批准人、审核人、及主检人签名无效。
4. The report is invalid when anything of following happens – illegal transfer, reproduce, embezzlement, imposture, modification or tampering in any media form.
私自转让、复制、盗用、冒用、涂改、或以任何媒体形式篡改的报告书无效。
5. Objections to the test report must be submitted to TCT within 15 days.
对报告书若有异议，应于收到报告之日起 15 天内向本公司提出。
6. The test report is valid for the tested samples only.
本报告仅对测试样品有效。
7. The Chinese contents in this report are only for reference.
本报告中的中文内容仅供参考。

*******End of Report 报告结束*******